

TE106 Epoxy Matrix CFRP

Super Resin, Inc.

Headquarters | 2283 Sakahama, Inagi,
Tokyo 206-0822 Japan

TEL +81-42-331-3611 FAX +81-42-331-3100

Tsukui Advanced Factory | 3512 Nagatake, Midori-ku, Sagami-hara
Kanagawa 252-0154 Japan

TEL +81-42-780-5003 FAX +81-42-780-2445

Laminate Data T-300 3K 200g/m² Plain Weave

Properties	Method	Results
Tensile Strength	JIS K 7164	773 MPa
Tensile Modulus	JIS K 7164	65.0 GPa
Compression Strength	JIS K 7076	705 Mpa
Short Beam Share Strength	JIS K 7057	66.6 Mpa

※ VF=56%

Typical Neat Resin Data

Color : Yellow

T_g : 143.2°C

(Measure by DMA E')

